



15 July 1994

**CHEMICAL
PHYSICS
LETTERS**

Chemical Physics Letters 224 (1994) 233–237

Electron spin relaxation of the PO_3^{2-} radical in ferroelectric betaine phosphite and in the proton glass betaine phosphate/betaine phosphite

A. Pöpl^a, G. Völkel^a, J. Hoentsch^a, S. Orlinski^b, A. Klöpperpieper^c

^a Fakultät für Physik und Geowissenschaften, Universität Leipzig, D-04103 Leipzig, Germany

^b Physical Faculty, Kasan State University, Kasan, Russian Federation

^c Fachbereich Physik, Universität des Saarlandes, D-66123 Saarbrücken, Germany

Received 21 March 1994; in final form 10 May 1994

Abstract

Measurements of the electron spin–lattice relaxation time T_1 and the phase memory time T_M of the PO_3^{2-} radical in γ -irradiated betaine phosphite and betaine phosphate/betaine phosphite are presented. The temperature dependence of T_1 indicates the interaction of the electron spin with two groups of optical branches via Raman processes in both crystals. An additional relaxation path due to the interaction with two-level local tunneling states has been observed in the mixed crystal confirming glassy behaviour. The T_M temperature dependence reflects thermally activated local motional effects of the PO_3 group in both crystals.

1. Introduction

The molecular crystals betaine phosphite (BPI) $(\text{CH}_3)_3\text{NCH}_2\text{COO}\cdot\text{H}_3\text{PO}_3$ and betaine phosphate (BP) $(\text{CH}_3)_3\text{NCH}_2\text{COO}\cdot\text{H}_3\text{PO}_4$ belong to the well known family of betaine addition compounds that shows an impressive variety of ordered low-temperature phases [1,2]. Thus BPI transforms at $T_C=216$ K from an antiferrodistortive room temperature phase into a ferroelectric low-temperature phase [3,4] whereas BP exhibits below $T_C=86$ K antiferroelectric ordering [5]. The room temperature phase of BP is also antiferrodistortive. In solid solutions BP/BPI the competing antiferroelectric and ferroelectric interactions lead to a suppression of the long-range electric order. Proton glass behaviour has recently been observed [6] in mixed crystals of intermediate concentrations BP:BPI(40/60).

We showed in a previous paper [7] that PO_3^{2-} rad-

icals can be formed by γ irradiation of BPI. The proton H14 is removed by γ irradiation from the H_3PO_3 group and one unpaired electron remains in this non-bonding phosphorus sp^3 orbital. In this Letter, we examine the electron spin relaxation of the paramagnetic PO_3^{2-} probe in a pure BPI single crystal and in a mixed single crystal BP:BPI(40/60) by means of electron spin echo (ESE) technique. Both the spin–lattice relaxation (SLR) time T_1 and the phase memory time T_M of the PO_3^{2-} centre have been investigated in the temperature range $4 \leq T \leq 300$ K. T_M is a measure of the spin–spin relaxation (SSR) time.

2. Experimental

The ESE measurements were carried out on a BRUKER ESP 380 FT-EPR spectrometer and on a homebuilt ESE spectrometer both working at X band