

The rare-earth centers in CsCdBr₃

J. Heber^{a,*}, R. Demirbilek^a, M. Altwein^a, B.Z. Malkin^b, V.F. Tarasov^c

^aDarmstadt University of Technology, D-64289 Darmstadt, Germany

^bKazan State University, 420008 Kazan, Russia

^cKazan Physicotechnical Institute, Kazan Science Center of the Russian Academy of Sciences, 420029 Kazan, Russia

Abstract

CsCdBr₃ crystallizes in the quasi-linear CsNiCl₃ structure. It possesses linear chains of [CdBr₆]⁴⁻ octahedra separated by parallel chains of Cs⁺. Trivalent rare-earth (RE) ions substitute for the divalent Cd ions. The need for charge compensation leads to a number of RE centers, the most prominent of which is the symmetric pair center RE³⁺–(Cd vacancy)–RE³⁺. Madelung calculations were performed for a number of different centers giving a ranking for their chance of realization. Experimental evidence from optical spectroscopy and submillimeter ESR is given for the most likely centers. The symmetric pair center is of special interest for cooperative phenomena of RE³⁺ ions. This includes direct ion–ion interactions and interactions with or via the electronic excitations of the host lattice. Some experiments are discussed. © 2002 Elsevier Science B.V. All rights reserved.

Keywords: Rare-earth centers; CsCdBr₃

1. Introduction

CsCdBr₃ is not just another host material for rare-earth (RE) ions. It possesses a number of specific properties which are more of fundamental than of direct technological interest.

1. Trivalent RE ions substitute for divalent Cd ions. This requires charge compensation in a very dense crystal structure not offering the chance of charge compensation by interstitial ions such as, for example, in CaF₂. Charge compensation can only be realized by ion vacancies. The most discussed center of this kind is the symmetric pair center RE³⁺–(Cd vacancy)–RE³⁺. This was proposed in 1977 [1] on the basis of ESR experiments on CsCdBr₃:Gd³⁺.
2. CsCdBr₃ has a quasi-linear structure with face-sharing [CdBr₆]⁴⁻ octahedra separated by chains of [CsBr₁₂] anticubes. The symmetry of the Cd²⁺ sites is almost cubic with a slight trigonal distortion along the C₃ axis of the chain. The triangular basis of both chains, Cs and

- Cd, is identical. Therefore, the crystal readily tends to stacking faults continuing from one chain to the other.
3. [CdBr₆]⁴⁻ complexes are strongly bound due to an essential contribution from covalent bonding. Theoretical calculations [2] show that the band structure in the region of the energy gap is mainly determined by this complex. Thus, the excitonic states of the lattice are excited states of this complex. The excitons can be delocalized as well as localized at stacking faults and at dopant RE ions.
4. As a result of the selection rules for optical transitions of the [CdBr₆]⁴⁻ complex, the transitions from the valence to the lowest conduction band do not originate from the top of the valence band, but from lower branches. In this way, the optical band gap is much wider than the electronic one.
5. Because RE³⁺ ions substitute for Cd²⁺ in [CdBr₆]⁴⁻ octahedra, they are directly embedded in the exciton-forming complex. This explains the strong interaction of the excitons with the RE ions. Experimental evidence will be given for this.

2. Optical and ESR spectra

From standard ESR spectra of CsCdBr₃:Gd³⁺, we know of the existence of the symmetric pair centers RE³⁺–(Cd vacancy)–RE³⁺ [1]. But the number of transitions found in

*Corresponding author. Tel.: +49-6151-162-483; fax: +49-6151-164-883.

E-mail address: elpo@hrz1.hrz.th-darmstadt.de (J. Heber).